

least 30.

24. (New) The absorbent insert according to Claim 22, wherein the absorbent polymer has a retention of at least 25 g/g.

25. (New) The absorbent insert according to Claim 22, wherein the absorbent polymer has an absorption under pressure of at least 15 g/g.

26. (New) The absorbent insert according to Claim 22, wherein the soluble ratio of the absorbent polymer is 3.5 wt.-%.

27. (New) The absorbent insert according to Claim 22, wherein having a migration value of ≤ 15 mg/g.

28. (New) The absorbent insert according to Claims 22, wherein the top and bottom covering layer comprise a plastic or cellulose film, a fabric or a fleece; and

at least one part of the covering layer film is permeable to water or an aqueous liquid as a result of a perforation.

29. (New) Absorbent insert according to Claim 22, wherein the core comprises fleece, a fiber, a fabric;

wherein the polymer absorbing an aqueous liquid is dispersed and optionally fixed.

30. (New) Absorbent insert according to Claim 29, wherein the core has an arrangement in layers of the absorbent polymer part within the core of fiber and fabric.

31. (New) Absorbent insert according to Claim 29 or 30, wherein the fiber is a hollow fiber.

32. (New) Absorbent insert according to Claim 22, wherein the absorbent polymer is made from a partially neutralized monoethylenically unsaturated monomer containing an acid group and, optionally another monomer copolymerizable therewith;

wherein the absorbent polymer is further made from crosslinker as well as a polymer